

PRODUCT DESCRIPTION

Stontec ERF is a nominal 2 mm thick decorative flooring system with a stain-resistant surface. The colour-flake broadcast layer results in an attractive floor surface with unlimited colour options and is sealed with an epoxy sealer to form a seamless surface. It is comprised of:

Stonhard Primer

Appropriate primer for sealing and bonding to the substrate.

Stonshield Aggregate

Brightly-colored, quartz broadcast aggregate

ERF undercoat

A three-component, high-solids, epoxy undercoat consisting of resin, curing agent and filler

Stontec Flakes

Brightly-colored flakes

Stonkote CE4

A two-component, high-solids, high-performance, UV-resistant, clear epoxy sealer.

OPTIONS

Cove Base

To provide for an integral seal at the joint between the floor and the wall, cove bases in heights from 5 to 15 cm are available.

Thickness

For areas requiring increased thickness, a 3 to 5 mm of epoxy mortar may be added.

PACKAGING

Stontec ERF is packaged in units for easy handling. Each unit consists of:

Stonshield Aggregate

1 bag of colored quartz aggregate

Stontec ERF undercoat

0.66 carton containing:

6 foil bags of amine

6 poly bags of resin

0.66 boxes of undercoat filler

Stontec flakes

0.9 individual boxes of small (1.5 mm) colored flakes

or

0.7 individual boxes of large (6 mm) colored flakes

Stonkote CE4

1 carton containing:

6 foil bags of amine

6 poly bags of resin

IMPORTANT: Appropriate primer must be ordered separately depending on the substrate.

COVERAGE

Each unit of Stontec ERF will cover approximately 18.6 m² of surface at a 2 mm nominal thickness.

PHYSICAL CHARACTERISTICS

Tensile Strength.....	35 N/mm ²
(ASTM D-638)	
Flexural Modulus of Elasticity.....	1.1 x 10 ⁴ N/mm ²
(ASTM D-790)	
Hardness	85 to 90
(ASTM D-2240, Shore D)	
Impact Resistance	> 18 Nm
(ASTM D-4226)	
Abrasion Resistance	0.03 gm max. weight loss
(ASTM D-4060, CS-17)	
Cure Rate.....	12 hours for Foot traffic
(@25°C).....	24 hours for normal operations
Flexural Strength	27,6 N/mm ²
(ASTM D-790)	
Flammability.....	Class 1
(ASTM E-648)	
Linear Coefficient of	
Thermal Expansion	30x10 ⁻⁵ mm/m°C
(ASTM C-531)	
VOC Content	
(ASTM D-2369)	ERF Undercoat - 34 g/l
.....	Stonkote CE4 - 34 g/l

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

STORAGE CONDITIONS

Store all components of Stontec ERF between 16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container

COLOUR

Stontec ERF is available in 12 standard colors in small (1.5 mm) or large (6 mm) sized flakes. Refer to the Stonshield colour sheet. Custom colors are available upon request.

Note: Micro (0.8 mm) flakes are available upon special request.

SUBSTRATE

Stontec ERF, with the appropriate primer, is suitable for application over properly prepared concrete, wood, brick, quarry tile, metal or Stonhard Stonset grouts. For questions regarding other substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard's representative or Technical Service.

PRIMING

The use of the appropriate primer is necessary for all applications of Stontec ERF. The primer must be fully cured prior to application of the undercoat.

MIXING

- Proper mixing is critical for the products to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing is required for all components.
- See Stontec ERF Directions for further details.

APPLYING

- DO NOT attempt to install material if the temperature of Stontec ERF components and substrate are not within 16 to 30°C. The cure time and application properties of the material will be severely affected.
- The primer is mixed, applied to the floor and broadcasted to refusal with Stonshield aggregate. The primer is allowed to cure and excess aggregate is removed.
- The undercoat is mixed, applied to the floor and broadcasted to refusal with Stontec flakes. The undercoat is allowed to cure and excess flake is removed.
- Stonshield sealer is mixed, applied to the floor and allowed to cure. The floor is lightly sanded and vacuumed.
- A second Stonshield sealer is applied to the floor and allowed to cure.


Refer to the Stontec ERF Directions for further detail.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stontec Chemical Resistance Guide.
- Safety Data Sheets for Stontec ERF are available on line at www.stonhard.com under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard products.
- Requests for literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, highgloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant build up occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

CE MARKING

The harmonized European Standard EN 13813 „Screed material and floor screeds- Screed materials - Properties and requirements“ specifies the requirements for screed materials for use in floor construction internally. Resinous flooring systems as well as resinous screeds fall under this specification they have to be CE-labeled as per **Annex ZA., Table ZA.1.5 and 3.2** and fulfill the requirements of the given mandate of the Construction Products Regulation no. 305/2011

	
StonCor Europe Rue du Travail 9 1400 Nivelles, Belgium 13	
DOP-2013.06.001 EN 13813 SR-AR0.5-B2.0-IR18	
Synthetic resin flooring system for use internally in buildings (system as per Product Data Sheet)	
Reaction to fire:	C _{fl} -S ¹
Release of corrosive substances:	SR
Wear resistance:	AR0.5
Adhesion strength by pull-off test:	> B2.0
Impact resistance:	IR18
Chemical resistance:	CRG*
* CRG: see Stonhard Chemical Resistance Guide	

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev. 8/20
 © 2020 Stonhard www.stonhard.com



European Offices:

Belgium	+32 674 93 710	Spain	+34 933 623 785	Germany	+49 240 541 740
France	+33 160 064 419	Portugal	+351 227 535 642	The Netherlands	+31 165 585 200
Poland	+48 422 112 768	United Kindom	+44 1925 649 458	Italy	+39 022 53 751
		East Europe	+48 422 112 768		